

## FERRULA 14 RMP



|                         |   |
|-------------------------|---|
| TIPO DE ACERO:          | T-304   |
| TEMPERATURA DE TRABAJO: | -10°C + 150°C (EPDM)<br>-20°C + 120°C (Silicón) |
| TIPO DE CONEXIÓN:       | Clamp   |
| ACABADO:                | Ra ≤ 0.8 μm                                     |

| COMPOSICIÓN QUÍMICA (%) |      |      |      |       |      |       |      |    |
|-------------------------|------|------|------|-------|------|-------|------|----|
| 304                     | C    | SI   | MN   | P     | S    | Cr    | Ni   | Mo |
|                         | 0.08 | 1.00 | 2.00 | 0.045 | 0.03 | 18-20 | 8-11 | -  |

| PROPIEDADES MECÁNICAS |                        |                      |               |
|-----------------------|------------------------|----------------------|---------------|
| Elongation(%)         | Tensile Strenght (Mpa) | Yield Strenght (Mpa) | Hardness (HB) |
| Min. 35               | Min. 485               | Min. 170             | Máx. 90       |

## DIMENSIONES (mm)

| SIZE | A    | B     | C     | D    |
|------|------|-------|-------|------|
| 1"   | 50.5 | 25.5  | 29.5  | 19.1 |
| 1 ½" | 50.5 | 38.2  | 42.6  | 28.6 |
| 2"   | 64   | 50.9  | 55.7  | 33.3 |
| 2 ½" | 77.5 | 63.9  | 68.8  | 34.9 |
| 3"   | 91   | 76.3  | 81.9  | 36.5 |
| 4"   | 119  | 101.7 | 108.1 | 38.1 |

