


## 16A TAPÓN END CAP



TIPO DE ACERO:	T-304
ACABADO:	Ra ≤1.6 μm Ra ≤0.8 μm

COMPOSICIÓN QUÍMICA (%)								
304	C	SI	MN	P	S	Cr	Ni	Mo
	0.08	1.00	2.00	0.045	0.03	18-20	8-11	-

PROPIEDADES MECÁNICAS			
Elongation(%)	Tensile Strength (Mpa)	Yield Strength (Mpa)	Hardness (HB)
Min. 35	Min. 485	Min. 170	Máx. 90



SIZE	DIMENSIONES (mm)				
	A	B	C	D	E
1"	33.4	29.5	3.3	8.1	12.6
1 ½"	46.8	42.6	4	8.7	14.3
2"	60.5	55.7	4	10.4	16
2 ½"	73.9	68.8	4.8	11.9	18.2
3"	87.5	81.9	4.8	11.9	18.3
4"	114.5	108.1	6.3	14.2	20.6