



## CRUZ SOLDABLE 9W

|                |           |
|----------------|-----------|
| TIPO DE ACERO: | T-304     |
| CONEXIÓN:      | Soldable. |

| COMPOSICIÓN QUÍMICA (%) |      |      |      |       |      |       |      |      |
|-------------------------|------|------|------|-------|------|-------|------|------|
| 304                     | (C)  | (SI) | (MN) | (P)   | (S)  | (Cr)  | (Ni) | (Mo) |
|                         | 0.08 | 1.00 | 2.00 | 0.045 | 0.03 | 18-20 | 8-11 | -    |

| PROPIEDADES MECÁNICAS |                        |                      |               |
|-----------------------|------------------------|----------------------|---------------|
| Elongation(%)         | Tensile Strength (Mpa) | Yield Strength (Mpa) | Hardness (HB) |
| Min. 35               | Min. 485               | Min. 170             | Máx. 90       |

| SIZE | DIMENSIONES (mm) |       |
|------|------------------|-------|
|      | L1               | D     |
| ¾"   | 47.6             | 19    |
| 1"   | 47.6             | 25.4  |
| 1 ½" | 57.2             | 38.1  |
| 2"   | 76.2             | 50.8  |
| 2 ½" | 76.2             | 63.5  |
| 3"   | 82.6             | 76.2  |
| 4"   | 98.4             | 101.6 |

