

### Tee Soldable L7WWW




TIPO DE ACERO:	304 / 316L
CONEXIÓN:	Soldable

COMPOSICIÓN QUÍMICA (%)								
304	(C)	(Si)	(Mn)	(P)	(S)	(Cr)	(Ni)	(Mo)
	0.08	1.00	2.00	0.045	0.03	18-20	8-11	-

COMPOSICIÓN QUÍMICA (%)								
316	(C)	(Si)	(Mn)	(P)	(S)	(Cr)	(Ni)	(Mo)
	0.035	1.00	2.00	0.045	0.03	16-18	10-14	2-3

PROPIEDADES MECÁNICAS			
Elongation(%)	Tensile Strenght (Mpa)	Yield Strenght (Mpa)	Hardness (HB)
Min. 35	Min. 485	Min. 170	Máx. 90

### Dimensiones (mm)



SIZE	A	L1	T
1/2"	12.7	47.6	1.65
3/4"	19	47.6	1.65
1"	25.4	47.6	1.65
1.5"	38.1	57.2	1.65
2"	50.8	76.2	1.65
2.5"	63.5	76.2	1.65
3"	76.2	82.6	1.65
4"	101.6	98.4	2.1
6"	152.4	143	2.8
8"	203.2	178	2.8
10"	254	216	2.8