

Tapón SMS



TIPO DE ACERO:	T-304
CONEXIÓN:	Soldable

COMPOSICIÓN QUÍMICA (%)								
304	(C)	(Si)	(Mn)	(P)	(S)	(Cr)	(Ni)	(Mo)
	0.08	1.00	2.00	0.045	0.03	18-20	8-11	-

PROPIEDADES MECÁNICAS			
Elongation(%)	Tensile Strength (Mpa)	Yield Strength (Mpa)	Hardness (HB)
Min. 35	Min. 485	Min. 170	Máx. 90

Dimensiones (mm)

SIZE	AD	BD	L	L1	L2
1"	35	31	8	4	4
1.5"	55	47	8	4	4
2"	65	59.5	9	4	5
2.5"	80	73	9	4	5
3"	93	86	10	5	5
4"	118	111.5	10	5	5

