

Tee Reducida L7 RWWW



TIPO DE ACERO:	304 / 316L
CONEXIÓN:	Soldable

COMPOSICIÓN QUÍMICA (%)								
304	(C)	(Si)	(Mn)	(P)	(S)	(Cr)	(Ni)	(Mo)
	0.08	1.00	2.00	0.045	0.03	18-20	8-11	-

COMPOSICIÓN QUÍMICA (%)								
316	(C)	(Si)	(Mn)	(P)	(S)	(Cr)	(Ni)	(Mo)
	0.035	1.00	2.00	0.045	0.03	16-18	10-14	2-3

PROPIEDADES MECÁNICAS			
Elongation(%)	Tensile Strenght (Spa)	Yield Strenght (Mpa)	Hardness (HB)
Min. 35	Min. 485	Min. 170	Máx. 90

Dimensiones (mm)

SIZE	C	L
1.5" x 1.0"	54.1	57.2
2.0" x 1.0"	59.2	76.2
2.0" x 1.5"	63.5	76.2
2.5" x 1.0"	63.5	76.2
2.5" x 1.5"	63.5	76.2
2.5" x 2.0"	82.6	76.2
3.0" x 1.0"	76.2	82.6
3.0" x 1.5"	76.2	82.6
3.0" x 2.0"	88.9	82.6
3.0" x 2.5"	82.6	82.6
4.0" x 1.0"	101.6	98.6
4.0" x 1.5"	101.6	98.6
4.0" x 2.0"	101.6	98.6
4.0" x 2.5"	95.3	98.6
4.0" x 3.0"	95.3	98.6
6.0" x 3.0"	120.7	127.0
6.0" x 4.0"	120.7	127.0

